

Expert finishes for wood and metal

Rustins Ltd, Waterloo Road, London NW2 7TX. Tel: +44 (0)20 8450 4666 www.rustins.co.uk

February 2018

PRODUCT DATA SHEET

Product Type A two part wood filler. Provides a strong long lasting repair for all interior and exterior wood work Available in Natural and White colour. Intended Use For all types of interior and exterior timber. The filler hardens within 30 mins at ambient temperature. It can be sanded, drilled, machined an planed and is particularly useful for carrying out repairs to edges on joinery where high strength needed. It is also suitable for marine applications. Preparation The surface must be clean, dry and free from all traces of oil, grease and dust. To provide good adhesion to timber, key the surface by lightly sanding with a medium grade of sand paper. Mix the filler with the hardener on a non-porous surface using an amount of filler the size of a good ball to a pea-sized ball of hardener as the mixing ratio. Mix thoroughly until an even colour is obtained. Do not prepare more than is required as any excess will be unusable after 10 mins. Applicator Applicator Applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance Compatibility Compatible under all Rustins finishes.
Intended Use For all types of interior and exterior timber. The filler hardens within 30 mins at ambient temperature. It can be sanded, drilled, machined ar planed and is particularly useful for carrying out repairs to edges on joinery where high strength needed. It is also suitable for marine applications. Preparation The surface must be clean, dry and free from all traces of oil, grease and dust. To provide good adhesion to timber, key the surface by lightly sanding with a medium grade of sand paper. Mix the filler with the hardener on a non-porous surface using an amount of filler the size of a go ball to a pea-sized ball of hardener as the mixing ratio. Mix thoroughly until an even colour is obtained. Do not prepare more than is required as any excess will be unusable after 10 mins. Mix using the applicator provided or use a putty knife but apply using the applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time 30 mins – 1 hr depending on temperature and humidity. Re-coating Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage Maintenance N/A
The filler hardens within 30 mins at ambient temperature. It can be sanded, drilled, machined ar planed and is particularly useful for carrying out repairs to edges on joinery where high strength needed. It is also suitable for marine applications. Preparation The surface must be clean, dry and free from all traces of oil, grease and dust. To provide good adhesion to timber, key the surface by lightly sanding with a medium grade of sand paper. Mix the filler with the hardener on a non-porous surface using an amount of filler the size of a go ball to a pea-sized ball of hardener as the mixing ratio. Mix thoroughly until an even colour is obtained. Do not prepare more than is required as any excess will be unusable after 10 mins. Mix using the applicator provided or use a putty knife but apply using the applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage Mix Maintenance N/A
Preparation The surface must be clean, dry and free from all traces of oil, grease and dust. To provide good adhesion to timber, key the surface by lightly sanding with a medium grade of sand paper. Mix the filler with the hardener on a non-porous surface using an amount of filler the size of a go ball to a pea-sized ball of hardener as the mixing ratio. Mix thoroughly until an even colour is obtained. Do not prepare more than is required as any excess will be unusable after 10 mins. Mix using the applicator provided or use a putty knife but apply using the applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance N/A
Application Applic
Application ball to a pea-sized ball of hardener as the mixing ratio. Mix thoroughly until an even colour is obtained. Do not prepare more than is required as any excess will be unusable after 10 mins. Mix using the applicator provided or use a putty knife but apply using the applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time 30 mins – 1 hr depending on temperature and humidity. Re-coating Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance N/A
Applicator provided. Apply sufficient filler so that it is proud of the surface to allow a continuous smooth surface to be obtained by sanding. Curing Time 30 mins – 1 hr depending on temperature and humidity. Re-coating Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance N/A
Re-coating Time Once fully cured and after sanding back, most paints can be applied. Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance N/A
Application Temp. Ideally 15-25°C, but do not use below 10°C. Coverage N/A Maintenance N/A
Coverage N/A Maintenance N/A
Maintenance N/A
Compatibility Compatible under all Rustins finishes.
Settlement N/A
Shelf-life/Storage 18 months if stored under the recommended conditions. Store in cool and dry place below 25 deg C.
Harmful by inhalation. Contains Styrene. Do not breathe vapours. Wear suitable protective gloves and eye/face protection. A full Health and Safety Data Sheet is available on request or on www.rustins.co.uk
Clean-Up All tools must be cleaned immediately after use with Rustins Cellulose Thinners before product sets hard.
Sizes 250g 500g 1000g